


Tablas de resistencia a la ruptura de los cables de acero



SERIE 6 x 24		TIPO BALLENA	
Diámetro		Alma de Fibra	
mm.	plg.	Peso Kg/mts	Resistencia Ruptura en toneladas
6.4	1/4	0.13	1.92
8.0	5/16	0.22	2.88
9.5	3/8	0.29	3.77
11.5	7/16	0.39	5.36
13.0	1/2	0.52	6.63
14.5	9/16	0.66	8.37
16.0	5/8	0.80	10.27
19.0	3/4	1.16	14.70
22.0	7/8	1.65	19.90
26.0	1	2.05	25.90
29.0	1-1/8	2.60	32.50
32.0	1-1/4	3.21	40.00
35.0	1-3/8	3.88	48.10
38.0	1-1/2	4.63	57.10

Principales abreviaturas

FW	Filler Wire Construcción - Construcción Filler Wire.
PS	Plow Steel - Acero tipo "Arado"
IPS	Improved Plow Steel - Acero tipo "Arado" mejorado
EIPS	Extra Improved Plow Steel - Acero "Arado" extramejorado
PF	Preformed - Preformado