


Tablas de resistencia a la ruptura de los cables de acero



Diámetro		No. Parte	Alma de Fibra	
mm	plg		Peso kg/m	Resistencia Ruptura en toneladas
6.4	1/4"	-	0.14	1.64
8.0	5/16"	10237	0.22	2.86
9.5	3/8"	8504	0.33	4.48
11.1	7/16"	8506	0.41	5.42
13.0	1/2"	5479	0.55	7.57
14.5	9/16"	9007	0.74	8.40
16.0	5/8"	8505	0.86	11.50
19.0	3/4"	-	1.22	16.20
22.0	7/8"	-	1.79	19.10
26.0	1"	-	2.34	24.50

Principales abreviaturas

FW	Filler Wire Construcción - Construcción Filler Wire.
PS	Plow Steel - Acero tipo "Arado"
IPS	Improved Plow Steel - Acero tipo "Arado" mejorado
EIPS	Extra Improved Plow Steel - Acero "Arado" extramejorado
PF	Preformed - Preformado