


## Tablas de resistencia a la ruptura de los cables de acero



SERIE 19 x 7		TIPO ELEFANTE		
Diámetro		Alma de Acero		
mm	plg	Peso kg/m	Resistencia Ruptura en toneladas	
			IPS	EIPS
6.4	1/4"	0.20	2.26	2.51
8.0	5/16"	0.31	3.53	3.90
9.5	3/8"	0.39	5.07	5.58
11.1	7/16"	0.52	6.88	7.56
13.0	1/2"	0.67	8.94	9.80
14.5	9/16"	0.86	11.20	12.30
16.0	5/8"	1.06	13.90	15.20
19.0	3/4"	1.52	19.80	21.80
22.0	7/8"	2.07	26.80	29.50
26.0	1"	2.71	34.70	38.30
29.0	1-1/8"	3.42	43.70	48.20
32.0	1-1/4"	4.23	53.70	59.10

### Principales abreviaturas

FW	Filler Wire Construcción - Construcción Filler Wire.
PS	Plow Steel - Acero tipo "Arado"
IPS	Improved Plow Steel - Acero tipo "Arado" mejorado
EIPS	Extra Improved Plow Steel - Acero "Arado" extramejorado
PF	Preformed - Preformado